



P O L S K A N O R M A

ICS 77.040.10

PN-EN ISO 16859-3

Wprowadza
EN ISO 16859-3:2015, IDT
ISO 16859-3:2015, IDT

Zastępuje
—

Metale

Pomiar twardości sposobem Leeba

Część 3: Kalibracja wzorców odniesienia

Norma Europejska EN ISO 16859-3:2015 *Metallic materials – Leeb hardness test – Part 3: Calibration of reference test blocks (ISO 16859-3:2015)* ma status Polskiej Normy

© Copyright by PKN, Warszawa 2015

nr ref. PN-EN ISO 16859-3:2015-12

Wszelkie prawa autorskie zastrzeżone. Żadna część niniejszej publikacji nie może być zwielokrotniana jakkolwiek techniką bez pisemnej zgody Prezesa Polskiego Komitetu Normalizacyjnego

ISBN 978-83-275-5353-9

PN-EN ISO 16859-3:2015-12

Przedmowa krajowa

Niniejsza norma została zatwierdzona przez Prezesa PKN dnia 10 grudnia 2015 r.

Komitetem krajowym odpowiedzialnym za normę jest KT nr 123 ds. Badań Własności Metali.

Istnieje możliwość przetłumaczenia normy na język polski na wniosek zainteresowanych środowisk. Decyzję podejmuje właściwy Komitet Techniczny.

Odpowiedniki krajowe norm i innych dokumentów powołanych w niniejszej normie można znaleźć w katalogu Polskich Norm. Oryginały norm i innych dokumentów powołanych są dostępne w PKN.

W sprawach merytorycznych dotyczących treści normy można zwracać się do właściwego Komitetu Technicznego lub właściwej Rady Sektorowej PKN, kontakt: www.pkn.pl

Nota uznaniowa

Norma Europejska EN ISO 16859-3:2015 została uznana przez PKN za Polską Normę PN-EN ISO 16859-3:

EUROPEAN STANDARD

EN ISO 16859-3

NORME EUROPÉENNE

EUROPÄISCHE NORM

October 2015

ICS 77.040.10

English Version

Metallic materials - Leeb hardness test - Part 3: Calibration of reference test blocks (ISO 16859-3:2015)

Matériaux métalliques - Essai de dureté Leeb - Partie 3
: Etalonnage des blocs de référence (ISO 16859-
3:2015)

Metallische Werkstoffe - Härteprüfung nach Leeb - Teil
3: Kalibrierung von Härtevergleichsplatten (ISO
16859-3:2015)

This European Standard was approved by CEN on 10 July 2015.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

EN ISO 16859-3:2015 (E)

Contents

Page

European foreword.....	3
-------------------------------	----------

European foreword

This document (EN ISO 16859-3:2015) has been prepared by Technical Committee ISO/TC 164 “Mechanical testing of metals” in collaboration with Technical Committee ECISS/TC 101 “Test methods for steel (other than chemical analysis)” the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 2016, and conflicting national standards shall be withdrawn at the latest by April 2016.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 16859-3:2015 has been approved by CEN as EN ISO 16859-3:2015 without any modification.

INTERNATIONAL
STANDARD

ISO
16859-3

First edition
2015-09-15

**Metallic materials — Leeb hardness
test —**

**Part 3:
Calibration of reference test blocks**

*Matériaux métalliques — Essai de dureté Leeb —
Partie 3: Etalonnage des blocs de référence*



Reference number
ISO 16859-3:2015(E)

© ISO 2015

ISO 16859-3:2015(E)



COPYRIGHT PROTECTED DOCUMENT

© ISO 2015, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Manufacture of reference test blocks	1
4 Calibration machine	2
4.1 General.....	2
4.2 Traceability.....	2
4.3 Requirements on calibration machines.....	2
4.4 Calibration of calibration machines.....	3
5 Calibration procedure	4
6 Number of test indentations	4
7 Uniformity of hardness	4
8 Marking	6
9 Validity	6
Annex A (normative) Requirements for Leeb hardness calibration machines	7
Annex B (informative) Measurement uncertainty of reference test block	8
Annex C (informative) Examples of reference test block	12
Bibliography	13

ISO 16859-3:2015(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary Information](#)

The committee responsible for this document is ISO/TC 164, *Mechanical testing of metals*, Subcommittee SC 3, *Hardness testing*.

ISO 16859 consists of the following parts, under the general title *Metallic materials — Leeb hardness test*:

- *Part 1: Test method*
- *Part 2: Verification and calibration of the testing devices*
- *Part 3: Calibration of reference test blocks*

Metallic materials — Leeb hardness test —

Part 3: Calibration of reference test blocks

1 Scope

This part of ISO 16859 specifies a method for the calibration of reference test blocks that are used for the indirect verification of Leeb hardness testers according to ISO 16859-2 and for the periodic checking according to ISO 16859-1.

The procedures necessary to ensure metrological traceability of the calibration machine are also specified.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 16859-1, *Metallic materials — Leeb hardness test — Part 1: Test method*

ISO 16859-2, *Metallic materials — Leeb hardness test — Part 2: Verification and calibration of the testing devices*

ISO/IEC 17025, *General requirements for the competence of testing and calibration laboratories*

3 Manufacture of reference test blocks

3.1 The block shall be specially manufactured for use as a reference test block.

Attention is drawn to the need to use a manufacturing process which will give the necessary homogeneity, stability of texture and uniformity of surface hardness.

3.2 The uniformity of the metallic reference test block shall meet the requirements specified in [7.2](#) and [Table 3](#).

3.3 The impact nature of a Leeb test requires a reference test block with a minimum mass and thickness, as specified in [Table 1](#).

NOTE Examples of common dimensions of reference test blocks are specified in [Annex C](#).

ISO 16859-3:2015(E)**Table 1 — Mass and thickness requirements of reference test block**

Type of impact devices	Minimum thickness mm	Minimum diameter mm	Minimum mass kg
D, DL, D+15, S, E, C	33	85	2,7
G	65	115	6,0

3.4 The reference test blocks shall be free of magnetism prior to calibration.

3.5 The maximum deviation from surface flatness of the top and bottom surfaces shall not exceed 0,01 mm. The surfaces of the blocks shall not be convex.

The maximum deviation from parallelism of the top and bottom surfaces shall not exceed 0,02 mm per 50 mm.

3.6 The test surfaces shall be free from damage, such as notches, scratches, oxide layers, etc., which interfere with the mechanics of the indentation process.

The mean surface roughness, R_a , [2] of the test surface(s) shall not exceed 0,1 μm . The sampling length, l , is 0,80 mm (see ISO 4287:1997, 3.1.9).

3.7 To provide evidence that no material is removed from the test surface(s) of the reference test block subsequent to calibration, the thickness at the time of calibration shall be marked on the test surface(s) or printed on the calibration certificate to an accuracy of 0,1 mm. Alternatively, a mark shall be placed on both the top and bottom surfaces, see [8.1 e](#)).

4 Calibration machine

4.1 General

In addition to fulfilling the general conditions specified in ISO 16859-2:2015, Clause 3, the calibration machine shall also meet the requirements given in [4.2](#) to [4.4](#).

4.2 Traceability

4.2.1 Leeb primary hardness standard machines owned by national level institutions are used to calibrate primary reference test blocks in Leeb hardness for accredited Leeb hardness calibration laboratories according to ISO/IEC 17025.

4.2.2 The instruments used for the verification and calibration of the Leeb hardness calibration machine shall be traceable to national standards.

NOTE A four-level structure of the metrological chain is necessary to define and disseminate hardness scales. The metrological chain of hardness values obtained by the Leeb method is defined in ISO 16859-1:2015, Figure C.1.

4.3 Requirements on calibration machines

4.3.1 Requirements on Leeb hardness calibration machines are given in [Annex A](#).

4.3.2 The resolution of Leeb hardness calibration machines shall be equal to or better than 1,0 HL.

4.4 Calibration of calibration machines

4.4.1 Leeb hardness calibration machines shall be calibrated at an interval of <12 months.

4.4.2 Leeb hardness calibration machines shall comply with the requirements defined in [Annex A](#).

4.4.3 Following direct calibration, an indirect calibration shall be conducted with at least three primary reference test blocks that cover the complete range of the Leeb hardness scale, as defined in [Table 2](#).

Table 2 — Leeb hardness ranges, minimum repeatability, and limiting error of calibration machines

Type of impact device	Leeb hardness range for indirect calibration HL ^a	Minimum repeatability W _H %	Limiting error G _H %
D, D+15	<500	1,0	±2,0
	500 to 700	1,0	±1,5
	>700	1,0	±1,0
DL, S	<700	1,0	±2,0
	700 to 850	1,0	±1,5
	>850	1,0	±1,0
C, E	<600	1,0	±2,0
	600 to 750	1,0	±1,5
	>750	1,0	±1,0
G	<450	1,0	±2,0
	450 to 600	1,0	±1,5
	>600	1,0	±1,0

^a HLD for impact devices D, HLD+15 for impact devices D+15, HLDL for impact devices DL, HLS for impact devices S, HLC for impact devices C, HLE for impact devices E, HLG for impact devices G.

Indirect calibration comprises at least 10 readings on each reference test block.

4.4.4 Calculation of error and repeatability of indirect calibration:

$$\bar{H} = \frac{1}{n} \sum_{i=1}^n H_i \quad (1)$$

where

\bar{H} is the Leeb hardness mean value;

H_i is the single Leeb hardness reading.

$$b_H = \frac{1}{n} \sum_{i=1}^n H_i - H_{CRM} \quad (2)$$

where

H_{CRM} is the Leeb hardness of primary reference test block;

b_H is the error of Leeb hardness.

ISO 16859-3:2015(E)

In indirect calibration, requirements concerning the limiting error of Leeb hardness are met when

$$G_H \geq |b_H(H)| + u_{CRM} \quad (3)$$

where

G_H is the limiting error of Leeb hardness (see [Table 2](#));

u_{CRM} is the calibration uncertainty of primary reference test blocks according to the calibration certificate for $k = 1$.

Standard deviation, s_H

$$s_H = \sqrt{\frac{1}{n-1} \sum_{i=1}^n (H_i - \bar{H})^2} \quad (4)$$

Variation coefficient, V_H

$$V_H = \frac{s_H}{\bar{H}} \cdot 100 \% \quad (5)$$

In indirect calibration, requirement concerning the minimum repeatability, W_H , (see [Table 2](#)) of Leeb hardness are met when:

$$W_H \geq V_H \quad (6)$$

where W_H is the minimum repeatability of Leeb hardness (see [Table 2](#)).

5 Calibration procedure

5.1 Reference test blocks are calibrated at a temperature of $(23 \pm 5) ^\circ\text{C}$ using Leeb hardness calibration machines conforming to [Clause 4](#), using the general procedure described in ISO 16859-1.

During calibration, thermal drift shall not exceed $1 ^\circ\text{C}$.

5.2 Reference test blocks are placed on a rigid steel plate of minimum thickness of 45 mm and minimum mass of 45 kg, and whose contact surface has been ground to a flatness of 0,01 mm or better. The reference test block is coupled to steel plate using a thin plastic film (thickness $< 0,1$ mm). The plastic film shall serve for adhesion between the block and the steel plate.

6 Number of test indentations

Leeb reference test blocks can be calibrated on both block surfaces (side A and side B). During a calibration sequence, 10 indentations are made evenly distributed over the entire test surface for each side. The calibration value is calculated as the arithmetic mean of 10 single readings. The calibration value is assigned to the respective test surface.

7 Uniformity of hardness

7.1 The Leeb hardness values of a test surface A of a reference test block are denoted H_1, H_2, \dots, H_{10} . If the block has two test surfaces, the Leeb hardness values of test surface B are denoted $H_{11}, H_{12}, \dots, H_{20}$. The arithmetic mean value(s) from the Leeb hardness calibration \bar{H}_A (and \bar{H}_B) are calculated using Formula (7) and Formula (8).

$$\bar{H}_A = \frac{H_1 + H_2 + \dots + H_{10}}{10} \quad (7)$$

$$\bar{H}_B = \frac{H_{11} + H_{12} + \dots + H_{20}}{10} \quad (8)$$

7.2 The variation coefficient provides the statistical parameter for the dispersion of the calibration values. Validity of results for the variation coefficients is defined in [Table 3](#).

Standard deviation:

$$s_{H_A} = \sqrt{\frac{\sum_{i=1}^{10} (H_i - \bar{H}_A)^2}{n-1}} \quad (9)$$

$$s_{H_B} = \sqrt{\frac{\sum_{i=11}^{20} (H_i - \bar{H}_B)^2}{n-1}} \quad (10)$$

Variation coefficient:

$$V_{H_A} = \frac{s_{H_A}}{\bar{H}_A} \cdot 100 \text{ in \%} \quad (11)$$

$$V_{H_B} = \frac{s_{H_B}}{\bar{H}_B} \cdot 100 \text{ in \%} \quad (12)$$

Table 3 — Maximum variation coefficient for reference test block calibrations

Type of impact device	Leeb hardness range of reference test block	Maximum variation coefficient
	HL ^a	%
D, D+15	<500	2,0
	500 to 700	1,5
	>700	1,0
DL, S	<700	2,0
	700 to 850	1,5
	>850	1,0
C, E	<600	2,0
	600 to 750	1,5
	>750	1,0
G	<450	2,0
	450 to 600	1,5
	>600	1,0

^a HLD for impact devices D, HLD+15 for impact devices D+15, HL_{DL} for impact devices DL, H_{LS} for impact devices S, H_{LC} for impact devices C, H_{LE} for impact devices E, H_{LG} for impact devices G.

7.3 Estimation of measurement uncertainty for reference test blocks is given in [Annex B](#).

ISO 16859-3:2015(E)

8 Marking

8.1 Reference test blocks shall at least hold the following marks (preferably in form of an engraving on the edge of the test surface):

- a) arithmetic mean value from Leeb hardness calibration incl. specification of device type, e.g. 799 HLD;
- b) name or mark of manufacturer or supplier of reference test block;
- c) serial number;
- d) name or mark of calibration agency;
- e) thickness of reference test block or markings on both test surfaces, respectively (see [3.7](#));
- f) year of calibration, if not indicated in the serial number.

8.2 The mark for test surface A (B) that is put on the side of the block shall be upright when the test surface A (B) is the upper face.

8.3 Reference test blocks shall hold accompanying documentation (a calibration certificate) providing the following information:

- a) a reference to this part of ISO 16859 , i.e. ISO 16859-3;
- b) identification of reference test block;
- c) single hardness values, arithmetic means and variation coefficients of reference test block;
- d) measurement uncertainty of calibration;
- e) date of calibration/date of issue.

9 Validity

Validity of a reference test block is limited to the testing conditions and for the impact device type used during calibration.

Validity of the calibration should be limited to five years. Attention is drawn to the fact that, for Al- and Cu-alloys, the calibration validity should be reduced to two to three years.

Annex A (normative)

Requirements for Leeb hardness calibration machines

A.1 Leeb hardness calibration machines according to the principle of velocity measurement

[Table A.1](#) gives the requirements for Leeb hardness calibration machines.

Table A.1 — Requirements on parameter implementation for Leeb hardness calibration machines

Parameter	Unit	Type of impact device						
		D	S	E	DL	D+15	C	G
Impact velocity, v_A	m/s	2,05	2,05	2,05	1,82	1,7	1,4	3,0
Maximum limiting deviation of impact velocity	m/s	$\pm 0,0025$	$\pm 0,0025$	$\pm 0,0025$	$\pm 0,002$	$\pm 0,002$	$\pm 0,002$	$\pm 0,005$
Mass of impact body, m	g	$5,45 \pm 0,03$	$5,40 \pm 0,03$	$5,45 \pm 0,03$	$7,25 \pm 0,03$	$7,75 \pm 0,03$	$3,1 \pm 0,03$	$20,0 \pm 0,03$
Radius of indenter ball, r	mm	$1,5 \pm 0,003$	$1,5 \pm 0,003$	$1,5 \pm 0,003$	$1,39 \pm 0,003$	$1,5 \pm 0,003$	$1,5 \pm 0,003$	$2,5 \pm 0,003$
Material of indenter		WC-Co ^a	C ^b	PCD ^c	WC-Co ^a	WC-Co ^a	WC-Co ^a	WC-Co ^a
Vickers hardness of indenter	HV2	1600 ± 50	1600 ± 50	≥ 4500	1600 ± 50	1600 ± 50	1600 ± 50	1600 ± 50
^a Tungsten-carbide cobalt. ^b Ceramics. ^c Polycrystalline diamond.								

ISO 16859-3:2015(E)

Annex B (informative)

Measurement uncertainty of reference test block

NOTE The structure of the metrological chain that is required to define and reproduce hardness scales is shown in ISO 16859-1:2015, Figure C.1.

B.1 Direct calibration and verification of Leeb hardness calibration machines

B.1.1 Calibration and verification of geometrical parameters of impact body and support ring

See ISO 16859-2:2015, 4.3.

B.1.2 Calibration and verification of signal of electronic unit

See ISO 16859-2:2015, 4.4.

B.2 Indirect calibration and verification of Leeb hardness calibration machines

NOTE In this Annex, "reference test block" is abbreviated as "certified reference material (CRM)".

The overall performance of Leeb hardness calibration machines is verified by indirect verification using primary reference test blocks. Also, this is used to determine the repeatability and error of the Leeb hardness calibration machine from the actual Leeb hardness.

The measurement uncertainty for the indirect verification^[3] of Leeb hardness calibration machine is calculated according to Formula (B.1):

$$u_{\text{CM}} = \sqrt{u_{\text{CRM-P}}^2 + u_{\text{xCRM-1}}^2 + u_{\text{CRM-D}}^2 + u_{\text{ms}}^2} \quad (\text{B.1})$$

where

- $u_{\text{CRM-P}}$ is the calibration uncertainty of primary reference test blocks according to the calibration certificate for $k = 1$;
- $u_{\text{xCRM-1}}$ is the standard uncertainty due to the repeatability of Leeb hardness calibration machine;
- $u_{\text{CRM-D}}$ is the standard uncertainty due to the change of Leeb hardness of primary reference test blocks since the last calibration, due to drift;
- u_{ms} is the standard uncertainty due to resolution of measuring system.

EXAMPLE See [Tables B.1, B.2, B.3, and B.4](#).

primary reference test block:	(767 ± 5,0) HLD
uncertainty of measurement of primary reference test block:	$u_{\text{CRM-P}} = 2,5$ HLD
temporal drift of primary reference test block:	$u_{\text{CRM-D}} = 0$
resolution of measurement system:	$\delta_{\text{ms}} = 1$ HLD

Table B.1 — Results of indirect calibration

Nr	Displayed Leeb hardness value HLD
1	763
2	768
3	767
4	768
5	764
6	767
7	765
8	767
9	770
10	769
Mean value	766,8
Standard deviation $s_{\times\text{CRM-1}}$	2,2
Standard measurement uncertainty $u_{\times\text{CRM-1}}$	0,74

$$u_{\times\text{CRM-1}} = \frac{t \cdot s_{\times\text{CRM-1}}}{\sqrt{n}} \quad (\text{B.2})$$

with Student's t-factor $t = 1,06$ for $n = 10$:

$$u_{\times\text{CRM-1}} = 0,74 \text{ HLD}$$

Table B.2 — Components of measurement uncertainty

Quantity	Estimated value	Standard measurement uncertainty	Type of distribution	Sensitivity coefficient	Contribution to uncertainty
X_i	x_i HLD	$u(x_i)$ HLD		c_i	$u_i(H)$ HLD
$u_{\text{CRM-P}}$	767	2,5	Normal	1,0	2,5
$u_{\times\text{CRM-1}}$	0	0,74	Normal	1,0	0,74
u_{ms}	0	0,29	Rectangular	1,0	0,29
$u_{\text{CRM-D}}$	0	0	Triangular	1,0	0
Combined measurement uncertainty u_{CM}					2,62
Expanded measurement uncertainty U_{CM} (where $k = 2$)					5,25

ISO 16859-3:2015(E)**B.3 Measurement uncertainty of reference test block**

The measurement uncertainty of reference test blocks^[3] is given by Formula (B.3):

$$u_{\text{CRM}} = \sqrt{u_{\text{CM}}^2 + u_{\text{xCRM-2}}^2} \quad (\text{B.3})$$

where

u_{CM} is the uncertainty of the Leeb hardness calibration machine;

$u_{\text{xCRM-2}}$ is the standard measurement uncertainty due to inhomogeneity of Leeb hardness of reference test block across the surface.

Table B.3 — Determination of inhomogeneity of reference test block

No	Calculated Leeb hardness value H_{CRM} HLD
1	764
2	770
3	768
4	768
5	765
6	770
7	766
8	767
9	772
10	771
Mean value	768,1
Standard deviation $s_{\text{xCRM-2}}$	2,6
Standard measurement uncertainty $u_{\text{xCRM-2}}$	0,87

Standard uncertainty CRM:

$$u_{\text{xCRM-2}} = \frac{t \cdot s_{\text{xCRM-2}}}{\sqrt{10}} \quad (\text{B.4})$$

using Student's t-factor $t = 1,06$ and $n = 10$:

$$u_{\text{xCRM-2}} = 0,87 \text{ HLD}$$

Table B.4 — Measurement uncertainty of reference test block

Leeb hardness of reference test block	Inhomogeneity of reference test block	Measurement uncertainty of Leeb hardness calibration machine	Expanded calibration uncertainty of reference test block
H_{CRM} HLD	$u_{\times\text{CRM}-2}$ HLD	u_{CM} HLD	U_{CRM} HLD
767	0,87	2,62	5,52

with

$$u_{\text{CRM}} = 2\sqrt{u_{\text{CM}}^2 + u_{\times\text{CRM}-2}^2}$$

Annex C (informative)

Examples of reference test block

[Table C.1](#) gives examples of common dimensions of reference test blocks.

Table C.1 — Mass and thickness of common reference test blocks

Type of impact devices	Minimum thickness mm	Minimum diameter mm	Minimum mass kg
D, DL, D+15, S, E, C	55	85	2,75
D, DL, D+15, S, E, C	33	115	2,7
G	65	115	6,0

Other dimensions can be used, if they satisfy the requirements of [3.2](#) and [3.3](#).

NOTE Additional examples of reference test block dimensions can be included in this part of ISO 16859 on request, subject to proof of usability.^[1]

Bibliography

- [1] YAMAMOTO T., YAMAMOTO M., TAKAGI S. *Current Status of Rebound Hardness Test Blocks in Japan and Outlook*, Proceedings of IMEKO 2010 TC3, TC5 and TC22 Conferences (2010) 379-382
- [2] ISO 4287, *Geometrical Product Specifications (GPS) — Surface texture: Profile method — Terms, definitions and surface texture parameters*
- [3] ISO/IEC Guide 98-3, *Uncertainty of measurement — Part 3: Guide to the expression of uncertainty in measurement (GUM:1995)*

ISO 16859-3:2015(E)

ICS 77.040.10

Price based on 13 pages

© ISO 2015 – All rights reserved