



P O L S K A N O R M A

ICS 25.160.40

PN-EN ISO 23278

Wprowadza

EN ISO 23278:2015, IDT
ISO 23278:2015, IDT

Zastępuje

PN-EN ISO 23278:2010

Badania nieniszczące spoin

Badania magnetyczno-proszkowe

Poziomy akceptacji

Norma Europejska EN ISO 23278:2015 *Non-destructive testing of welds – Magnetic particle testing – Acceptance levels (ISO 23278:2015)* ma status Polskiej Normy

© Copyright by PKN, Warszawa 2015

nr ref. PN-EN ISO 23278:2015-05

Wszelkie prawa autorskie zastrzeżone. Żadna część niniejszej publikacji nie może być zwielokrotniana jakkolwiek techniką bez pisemnej zgody Prezesa Polskiego Komitetu Normalizacyjnego

ISBN 978-83-275-4487-2

PN-EN ISO 23278:2015-05

Przedmowa krajowa

Niniejsza norma została zatwierdzona przez Prezesa PKN dnia 15 maja 2015 r.

Komitetem krajowym odpowiedzialnym za normę jest KT nr 165 ds. Spawania i Procesów Pokrewnych.

Istnieje możliwość przetłumaczenia normy na język polski na wniosek zainteresowanych środowisk. Decyzję podejmuje właściwy Komitet Techniczny.

Niniejsza norma zastępuje PN-EN ISO 23278:2010.

Odpowiedniki krajowe norm i innych dokumentów powołanych w niniejszej normie można znaleźć w katalogu Polskich Norm. Oryginały norm i innych dokumentów powołanych są dostępne w PKN.

W sprawach merytorycznych dotyczących treści normy można zwracać się do właściwego Komitetu Technicznego lub właściwej Rady Sektorowej PKN, kontakt: www.pkn.pl

Nota uznaniowa

Norma Europejska EN ISO 23278:2015 została uznana przez PKN za Polską Normę PN-EN ISO 23278:2015-05.

EUROPEAN STANDARD

EN ISO 23278

NORME EUROPÉENNE

EUROPÄISCHE NORM

March 2015

ICS 25.160.40

Supersedes EN ISO 23278:2009

English Version

Non-destructive testing of welds - Magnetic particle testing - Acceptance levels (ISO 23278:2015)

Contrôle non destructif des assemblages soudés - Contrôle
par magnétoscopie - Niveaux d'acceptation (ISO
23278:2015)

Zerstörungsfreie Prüfung von Schweißverbindungen -
Magnetpulverprüfung von Schweißverbindungen -
Zulässigkeitsgrenzen (ISO 23278:2015)

This European Standard was approved by CEN on 8 November 2014.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

EN ISO 23278:2015 (E)

Contents

Page

Foreword.....3

Foreword

This document (EN ISO 23278:2015) has been prepared by Technical Committee ISO/TC 44 "Welding and allied processes" in collaboration with Technical Committee CEN/TC 121 "Welding and allied processes" the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2015, and conflicting national standards shall be withdrawn at the latest by September 2015.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 23278:2009.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 23278:2015 has been approved by CEN as EN ISO 23278:2015 without any modification.

INTERNATIONAL
STANDARD

ISO
23278

Second edition
2015-03-01

**Non-destructive testing of welds —
Magnetic particle testing —
Acceptance levels**

*Contrôle non destructif des assemblages soudés — Contrôle par
magnétoscopie — Niveaux d'acceptation*



Reference number
ISO 23278:2015(E)

© ISO 2015

ISO 23278:2015(E)



COPYRIGHT PROTECTED DOCUMENT

© ISO 2015

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Testing parameters	1
5 Acceptance levels	2
5.1 General	2
5.2 Removal of imperfections	2
Annex A (informative) Recommended testing parameters	3
Bibliography	4

ISO 23278:2015(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT), see the following URL: [Foreword — Supplementary information](#).

The committee responsible for this document is ISO/TC 44, *Welding and allied processes*, Subcommittee SC 5, *Testing and inspection of welds*.

This second edition cancels and replaces the first edition (ISO 23278:2006), which has been technically revised.

Non-destructive testing of welds — Magnetic particle testing — Acceptance levels

1 Scope

This International Standard specifies acceptance levels for indications from imperfections in ferromagnetic steel welds detected by magnetic particle testing.

The acceptance levels are primarily intended for use during manufacture examination.

NOTE They can also be used for in-service inspection.

The acceptance levels in this International Standard are based on detection capabilities that can be expected when using techniques specified in ISO 17638 and parameters recommended in [Annex A](#). The acceptance levels can be related to welding standards, application standards, specifications or codes. Such a relationship is shown in ISO 17635 for ISO 5817.

Acceptance levels for grouped indications are not covered by this International Standard.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO/TS 18173, *Non-destructive testing — General terms and definitions*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO/TS 18173 and the following apply.

3.1

linear indication

l

indication having a length greater than three times its width

3.2

non-linear indication

d

indication having a length less than or equal to three times its width

4 Testing parameters

Many parameters, either individually or in combination, will affect the ability of a technique to detect imperfections of a given size and orientation with respect to the condition of the test surface.

Detection of small imperfections is highly dependent on the surface condition of the weld and the detection media used. Examples of the application of these parameters to give a high probability of detection are given in [Annex A](#).

ISO 23278:2015(E)

5 Acceptance levels

5.1 General

The width of the test surface shall include the weld metal and the adjacent parent metal up to a distance of 10 mm on each side.

Acceptance levels prescribed for linear indications are those corresponding to the evaluation level. Indications lower than this shall not be taken into account. Acceptable indications do not have to be recorded.

Any adjacent indications separated by less than the major dimension of the smaller shall be assessed as a single, continuous indication.

Local grinding may be used to improve the classification of all or just part of a test surface, when it is required to work to a higher detection limit than that expected by the existing weld surface condition.

Acceptance levels are given in [Table 1](#).

Table 1 — Acceptance levels for indications from imperfections

Dimensions in millimetres

Type of indication	Acceptance level ^a		
	1	2	3
Linear indication <i>l</i> = length of indication	$l \leq 1,5$	$l \leq 3$	$l \leq 6$
Non-linear indication <i>d</i> = major axis dimension	$d \leq 2$	$d \leq 3$	$d \leq 4$
^a Acceptance levels 2 and 3 may be specified with a suffix "X", which denotes that all linear indications detected shall be assessed to level 1. However, the probability of detection of indications smaller than those denoted by the original acceptance level can be low.			

5.2 Removal of imperfections

Where the product specification permits, local grinding may be used to reduce or remove imperfections which are the cause of unacceptable indications. All such areas shall be re-tested and evaluated with the same magnetic system and technique.

Annex A (informative)

Recommended testing parameters

Recommended testing parameters for reliable detection of small imperfections are given in [Table A.1](#). The surfaces are in the as-welded condition. It may be necessary to improve the surface condition, e.g. by abrasive paper or local grinding, to permit accurate interpretation of indications. The detection media are given in order of preference.

Table A.1 — Recommended testing parameters

Acceptance level	Surface condition	Detection media
1	Fine surface ^a	Fluorescent or colour contrast with contrast aid
2	Smooth surface ^b	Fluorescent or colour contrast with contrast aid
3	General surface ^c	Colour contrast with contrast aid or fluorescent with low sensitivity
^a The weld cap and parent material offer smooth clean surfaces with negligible undercut, rippling and spatter. The surface finish is typical of welds, made by automatic TIG-welding; submerged arc welding (fully mechanized) and manual metal arc welding with iron powder electrodes. ^b The weld cap and parent material offer reasonably smooth surfaces with minimal undercut, rippling and spatter. The surface finish is typical of welds made by manual metal arc welding vertical downwards and MAG-welding using argon rich gas for the capping runs. ^c The weld cap and parent material are in the as-welded condition. The surface finish is typical of welds made by manual metal arc welding or MAG-welding in any position.		

Bibliography

- [1] ISO 5817, *Welding — Fusion-welded joints in steel, nickel, titanium and their alloys (beam welding excluded) — Quality levels for imperfections*
- [2] ISO 17635, *Non-destructive testing of welds — General rules for metallic materials*
- [3] ISO 17638, *Non-destructive testing of welds — Magnetic particle testing*

ISO 23278:2015(E)

ICS 25.160.40

Price based on 4 pages

© ISO 2015 – All rights reserved